



PRODUCT DATA SHEET

Duraset-5 MMA 4:1 Spray

Introduction

HPS-6 Duraset is part of Ennis Traffic Safety Solution's High Performance Roadmarking product line. Based on proven methyl methacrylate (MMA) technology, the Duraset line consists of several white and yellow lead free products tailored for specific application methods, various film thicknesses and/or specific multi-component proportioning application equipment. All provide exceptional retroreflectivity and longevity at an attractive cost per useful life. Duraset provides outstanding adhesion to both concrete and asphalt and can be surface applied or inlaid for even greater durability. Optimum retroreflectivity is achieved when the proper reflective media and coating is used. Please consult with your sales representative for the best reflective media/Duraset combination.

Description

Duraset-5 is a "4:1" by volume ratio product designed for airless or air atomized spray application at a thickness of 30 mils or more. Spray is accomplished by using equipment designed to proportion by volume. One part of liquid catalyst, Part B, is blended into 4 parts of Part A methacrylate base, using a static mixer positioned just prior to the spray gun.

Duraset-5 may be applied at 30 to 90 mils for long line installation and intersection markings; and for inlay applications. Surface applications in excess of 120 mils are possible, applied in successive passes, and at a recommended maximum of 45 mils per pass. When applying Duraset-5 in thick films, in addition to drop on reflective media, it is advisable to blow reflective media into the spray fan for maximum long term retroreflectivity.

Storage Requirements

Avoid extreme storage temperatures. Keep materials in dry, protected areas, between 40°F – 80°F. Keep out of direct sunlight and protected from open flame. Use within six months of receipt.

Packaging and Mixing Instructions

Both A and B components of Duraset-5 come packaged at 50 gallons per drum. Each part is pumped into separate holding tanks on the application vehicle for automatic 4:1 metering, mixing and dispensing through the spray gun.

Installation

Refer to the "Application Guidelines" for surface preparation and temperature limitations. Refer to the

equipment manufacturers instructions for use of the application device, making sure to calibrate and check the calibration of the automatic metering.

Duraset-5 should be sprayed at a minimum of 30 mils thick when using it as a refresher coat. For inlay application, the material with reflective media shall be no closer than 10 mils to the surface of the substrate. If specifications require applying material above the plane of the road, it is recommended to extend the line width at least 1/16 of an inch beyond the edge of the inlay slot to keep the roadway edge from crumbling.

Long term retroreflectivity is most effective when the proper reflective media is used. Specific reflective types, composition, gradations, % rounds, and coatings have been tested and found to have superior performance when compared to “other” reflective media. The engineer and applicator shall confirm with the MMA manufacturer, which reflective product is currently the most effective.

For best results, reflective media should be dropped on at a rate of 10 to 12 pounds per 100 square feet depending upon type, gradation, and other factors. Please consult with your sales representative for the best reflective media/Duraset combination.

Handling and disposal of Duraset materials are covered in the SDS.

Typical Technical Data

TEST	RANGE	METHOD
Weight per gallon, A or B	14 lbs/gal minimum	D1475
Settling A	6 minimum	D869, 96 hours at 120 ° F
Pot life at 77 ° F (mix)	6 minutes minimum	80 cc of Part A, 20 cc of Part B
No track at 77 ° F (mix)	30 minutes max	D711, mixed as above, 60 mils thick
VOC (mix)	100 g/l maximum	D2205, mixed as above
Total solids (mix)	99% by weight min	As in VOC above
Adhesion (mix)	250 psi or substrate failure	D4541, mixed as above, 60 mils thick
Chemical resistance (mix)	Pass 7 days immersion	Cure 3 days – motor oil, diesel, ATF, salt, anti-freeze

SAFETY DATA SHEET AVAILABLE UPON REQUEST

Rev 11/23/2016

The Product Data offered herein is, to the best of our knowledge, true and accurate, but all recommendations are made without warning, expressed or implied. Because the conditions of use are beyond our control, neither Ennis Paint, Inc., nor its agents shall be liable for any injury, loss or damage, direct or consequential, arising from the use or the inability to use the product described herein. No person is authorized to make any statement or recommendation not contained in the Product Data Sheet, and any such statement or recommendation, if made, shall not bind the Corporation. Further, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents, and no license under the claims of any patent is either implied or granted.

Ennis Traffic Safety Solutions
5910 N. Central Expressway, Suite 1050
Dallas, Texas 75206
1-800-331-8118